


LITHIUM IRON PHOSPHATE BATTERY ——M87U



OUTLINE DIMENSION



L mm(")	W mm(")	H mm(")
530 (20.8)	440 (17.3)	132 (5.19)

ELECTRICAL PERFORMANCE

Nominal Voltage	51.2 V
Nominal Capacity	100Ah
Capacity @ 20A	300 min
Energy	5120 Wh
Communication	CAN/RS232/RS485
Resistance	≤45 mΩ @ 50% SOC
Efficiency	>96%
Module Parallel	Up to 10 packs

CHARGE PERFORMANCE

Recommended Charge Current	30A
Maximum Charge Current	100A
Recommended Charge Voltage	57.6V
BMS Charge Cut-Off Voltage	<58.4 V (3.65V/Cell)
Reconnect Voltage	>57.6 V (3.6V/Cell)
Balancing Voltage	<54.08V (3.38V/Cell)
Maximum Batteries in Series	16 (*Consult MOTOMA)

DISCHARGE PERFORMANCE

Maximum Continuous Discharge Current	100 A
Peak Discharge Current	110 A (1s)
BMS Discharge Cut-Off Current	150 A (100ms)
Balancing open voltage	54.4V (3.40V/Cell)
Recommended Low Voltage Disconnect	48V (3.0V/Cell)
BMS Discharge Cut-Off Voltage	43.2V (1s) (2.7V/Cell)
Reconnect Voltage	>49.6V (3.1V/Cell)
Short Circuit Protection	250 ~ 500 μs

MECHANICAL PERFORMANCE

Dimension (L x W x H)	530 x 440 x132 mm 20.8 x 17.3 x 5.19"
Approx. Weight	99.17 lbs(45Kg)
Terminal Type	DIN POST
Terminal Torque	80 ~ 100 in-lbs (9 ~ 11 N-m)
Case Material	SPCC
Enclosure Protection	IP21

TEMPERATURE PERFORMANCE

Discharge Temperature	-4 ~ 131 °F (-20 ~ 55 °C)
Charge Temperature	-4 ~ 113 °F (0 ~ 45 °C)
Storage Temperature	23 ~ 95 °F (-5 ~ 35 °C)
BMS High Temperature Cut-Off	149 °F (65 °C)
Reconnect Temperature	131 °F (55 °C)


COMPLIANCE

Certifications	CE (battery) UN38.3 (battery) UL1642 & IEC62133 (cells)
Shipping Classification	UN 3480, CLASS 9



LITHIUM IRON PHOSPHATE BATTERY ——M87U

SYSTEM DIAGRAM



FEATURES & BENEFITS



High cycle life

5000 cycles @80% DoD for effectively lower total of ownership cost



Longer service life

Low maintenance batteries with stable chemistry.



Built in circuit protection

Battery Management System (BMS) is incorporated against abuse.



Better storage

up to 6 months thanks to its extremely low self discharge (LSD) rate and no risk of sulphation.



Quickly recharge

Save time and increase productivity with less down time thanks to superior charge/discharge efficiency.



Extreme heat tolerance

Suitable for use in a wider range of applications where ambient temperature is unusually high: up to +60°C.



Lightweight

Lithium batteries provide more Wh/Kg while also being up to 1/3 the weight of its SLA equivalent.

APPLICATIONS

Lithium Iron Phosphate can be used in most applications that use Lead Acid, GEL or AGM type batteries. Suitable applications include:

- · Solar Storage
- Switching applications and more
- · Base transceiver station
- · Communication equipments
- · Central office
- Telecommunication systems
- · Electronic cash registers
- Microprocessor based office machine
- UPS

CAUTIONS

- Do NOT short circuit, reverse polarity, crush or disassemble.
- · Do NOT heat or incinerate.
- Do NOT immerse in any liquid.
- Store at 30~50% SOC. Recharging every 3 months is recommended. The storage area should be clean, cool, dry and ventilated.